

Piletop encapsulation epoxy resin system

Uses

This high performance fluid resin system is designed to encapsulate piletops and ensure water tightness. The applied product is continuously bonded to the pile surface and prevents water seepage either through capillaries or along the reinforcement path. When applied the product accepts the application of most types of self adhesive or torch applied membranes. The product is also compatible with most types of liquid applied membrane.

Advantages

- High strength and adhesion to substrate ensures excellent performance under operating conditions.
- Simple mixing techniques.
- Withstands attack by a wide range of chemicals, acids and alkalis, as well as ground water.
- High quality resins ensure durability and long term service life.
- Ensures piletop integrity as part of a waterproofing system.

Description

Supercast EPT is a fluid epoxy resin designed to encapsulate piletops in a range from 15-50 mm. It is supplied as a three component system consisting of base, hardener and specially processed fillers. The components are supplied in the correct mix proportions designed for whole pack mixing on site and no other materials should be added.

Properties

Usable life	: 2 hrs. @ 25°C 1 hr. @ 35°C
Density	: 1950 kg/m ³
Bond strength	: Greater than the tensile strength of concrete
Water penetration (BS EN 12390 P8)	: Nil
Rapid chl. permeability (AASHTO T 277-83)	: Negligible
Compressive strength ASTM C579 Method B (35°C cure)	: 75 N/mm ² @ 7 days
Tensile strength ASTM C307	: 11 N/mm ² @ 7 days
Flexural strength ASTM C580-Method A	: 20 N/mm ² @ 7 days

Instructions for use

Preparation

The formwork should be constructed to be leak proof as Supercast EPT is a fluid material. This can be achieved by using foam rubber strip or mastic sealant beneath the constructed formwork and between joints.

A heavy duty release agent should be applied to all contact areas of formwork.

Pile surface

This must be free from oil, grease, or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Rebar should be clean and rust free. If reprofiling is required Supercast PC** or Renderoc SXtra** may be used as appropriate.

All surfaces must be substantially dry. All free standing water must be removed.

Mixing

The entire contents of the hardener should be poured into the base container and mixed until homogeneous. Place the mixed base and hardener into a suitable mixer making sure that the entire volume is poured in. Add the aggregate and mix for 2-3 minutes or until uniform colour is achieved. Once mixed, the material must be used within the specified usable life (see under Properties). After this time, unused material will have stiffened and should be discarded.

Placing

Place the material within the usable life of the product. Continuous material flow is essential. Sufficient product must be available prior to starting and the time taken to pour a batch must be regulated to the time taken to prepare the next one.

Subsequent Applications

Prior to the application of any membrane to the piletop, the applied Supercast EPT should be lightly sanded to remove all traces of formwork release agent and provide an adhesion key.

Membranes should be subjected to an adhesion trial to ensure complete compatibility.

Cleaning

All tools and equipment should be cleaned with Fosroc Solvent 102* immediately after use.

Fosroc Supercast EPT

Technical support

Fosroc offers a comprehensive range of high performance, high quality construction products. Fosroc offers a technical support package to specifiers and contractors as well as technical advice from staff with unrivalled experience in the industry.

Estimating

Supply

Supercast EPT	:	10,14 & 20 litre packs
Fosroc Solvent 102	:	5 litre packs

Storage

Supercast EPT has a shelf life of 12 months if kept in a dry, cool store in the original unopened package.

Precautions

Health and safety

Some people are sensitive to epoxy resin so gloves and a barrier cream such as Kerodex 71, Rozalex 9, Debba-Wet Work or similar should be used when handling these products. If contact with the resin occurs, it must be removed before it hardens with a resin removing cream such as Kerocleanse 22 or Rozalex 42. Follow by washing with soap and water. **Do not** use solvent. The use of goggles is recommended but should accidental eye contamination occur, wash thoroughly with plenty of clean water and seek medical treatment immediately.

Fire

Fosroc Solvent 102 are flammable. No smoking. Use in well ventilated areas away from sources of heat and naked flames.

Flash points

Additional Information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

